



Confidential Report

Our Ref: 23/59005A/10/21





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 20 October 2021

Our Ref: 23/59005A/10/21

Your Ref: ---

Page: 1 of 4

Client:

Euroflam

Unit G1, Hazleton Interchange Industrial Estate
Lakesmere Road
Horndean
Hants
PO8 9JU

Job Title:

Fire Test on One Fabric Sample

Clients Order Ref:

--

Date of Receipt:

14 October 2021

Date Test Started:

19 October 2021

Description of Sample:

One sample of fabric, which was referenced by the client as;
353510. Kobe UK. Basoo & Malawi, stated to be 100% polyester.

Work Requested:

We were asked to make the following fire test:

BS 5852: Clause 11:2006 (2011)

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



1066

Note: This report relates only to the samples submitted and as described in the report.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 20 October 2021

Our Ref: 23/59005A/10/21
Your Ref: ---

Page: 2 of 4

Client: Euroflam

Testing BS 5852: Clause 11: 2006 (2011) Assessment of the ignitability of upholstered seating by Smouldering and Flaming sources – Source 5 (Crib 5)

Pre-Treatment

The material was subjected to the water soak procedure according to BS 5852:Annex E:2006 (2011).

Conditioning

The sample was conditioned and tested in the environments specified in Clause 10 of BS 5852: 2006 (2011).

Testing

The material was tested according to BS 5852:2006 (2011) Methods of test for the ignitability of upholstered composites for seating by flaming sources using Source 5 (Crib 5).

The sample was tested at 20°C and 71% relative humidity (R.H.).

The sample was tested over combustion modified polyurethane foam with a density of approximately 35-36kg/m³.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.

Date: 20 October 2021

Our Ref: 23/59005A/10/21
Your Ref: ---

Page: 3 of 4

Client: Euroflam

Results

The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

	Specimen 1	Specimen 2
Time of Ignition (s)	87	22
Time of Flame Extinction (s)	257	295
Time of Smoke Extinction (s)	389	413
Time of cover split	DNO	31
Extent of damage (mm) - Seat		
Width	122	115
Length	79	70
Depth	37	28
Extent of damage (mm) - Back		
Width	131	162
Length	296	297
Depth	45	63
Melting	No	No
Dripping	No	No
Charring	Yes	Yes
Comments and Observations		
Specimen Result (Ignition or Non-ignition)	Non-Ignition	Non-Ignition

Acronyms

ME – Manually extinguished
DNO – Did not observe time of events

EC – Escalating combustion
BTT – Burnt through thickness of foam

DNS – Material did not split
BTE – Burnt to extremities



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 20 October 2021

Our Ref: 23/59005A/10/21
Your Ref: ---

Page: 4 of 4

Client: Euroflam

Comment

The results indicate 'Non-Ignition' of the materials and the test is designated NI/5 (ie. Pass).

An estimation of uncertainty of measurement has been taken into account when making a judgment to any pass/fail criteria. Under our Policy we have used a non-binary decision rule.

See our Decision rules Policy (<http://www.bttg.co.uk/decision-rules-policy>) for further information.

Uncertainty Budget

Measurements: ± 2 mm

Timings: ± 2 seconds

Reported by:  B Bland, Technical Customer Services Officer

Countersigned by:  P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.