

## The Sidings Business Park, SKIPTON, North Yorkshire, BD23 1TB Phone or Fax 01756 792525



Office: 30 Alexandra Crescent, ILKLEY, West Yorkshire, LS29 9ER, Phone or Fax 01943 603459 Reg. No. 3168606, VAT No. 659 9604 77

# TEST CERTIFICATE

No. F14682/1

Assessment to BS 5867 : 2008 Specification for Fabrics for Curtains, Drapes and Window Blinds, Part 2 : Flammability Requirements using BS EN ISO 15025:2002

#### SAMPLE INFORMATION

Client Kobefab International, B.V.Vest 62, 5555 XP, Valkenswaard, 5550 AG, The

Netherlands.

Fabric Reference Moonlight FR Dim Out.

Dimensions 100cm by 142cm (Full width)

Date Received 4/8/2014
Pre-treatment None

Conditioning BS EN ISO 15025:2002 Clause 7.2.

### **TESTING**

Following the pre-treatment described above, the material was conditioned and tested according to BS EN ISO 15025:2002 Protective Clothing- Protection against heat and flame-Method of test for limited flame spread, using a 15 second flame application time and the results assessed according to the requirements of BS 5867: 2008 Specification for Fabrics for Curtains, Drapes and Window Blinds, Part 2: Flammability Requirements. Testing was carried out on the face side of the fabric.

	WARP			WEFT		
Specimen number	1	2	3	1	2	3
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris separated	No	No	No	No	No	No

It should be noted that the results may not apply to situations where there is a restricted air supply or prolonged exposure to intense heat as in a conflagration.

## **CONCLUSION**

The sample received meets BS 5867 : 2008 Specification for Fabrics for Curtains, Drapes and Window Blinds, Part 2, Flammability Requirements, Type B.

It should be noted that the fabric should be supplied with the manufacturers name, trademark or other identifying mark; the statement 'Flammability complies with the requirements of BS 5867: Part 2, Type B' and instructions on any special precautions to be taken concerning care (including cleansing) of the product to be manufactured from the fabric, preferably using an appropriate care labelling symbol in accordance with BS 2747 and taking account of the pre-treatment used in this test and the requirements of Clause 4 of BS 5867: Part 2: 2008.

END OF REPORT

Mr J Firth

**Technical Manager** 

711

END OF REPORT

#=Subcontracted to a UKAS accredited Test House. The results on this test report only relate to the specimens tested above.