

Wira House, West Park Ring Road,

Leeds, LS16 6QL, UK. Telephone: +44 (0)113 259 1999

> Email: info@bttg.co.uk Website: www.bttg.co.uk

Date: 26 November 2018

Our Ref: 55742-3 Your Ref: 1644

Page: 1 of 3

Client: Kobefab International B.V.

De Vest 62

5555 XP Valkenswaard

Netherlands

Job Title: Surface Ignition Of Curtains & Drapes (Type B)

Client's Order No: 1644

Date of Receipt: 16 November 2018
Date of Test Start: 22 November 2018

Description of Sample(s): One sample identified as follows was received for testing:

Oster CS, stated to be 100% Trevira CS

Work Requested: We were asked to make the following test:

BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk Website: www.bttg.co.uk

Date: 26 November 2018

Our Ref: 55742-3 Your Ref: 1644

Page: 2 of 3

Kobefab International B.V.

Sample was identified as follows:

Oster CS, stated to be 100% Trevira CS

BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds

Pre-treatment

No pre-treatment as this fabric is stated to be inherently flame retardant. BS 5867-2 Clause 6.3 states 'All fabrics shall be tested prior to any cleansing procedure. Except where specified that testing after an approved cleansing or wetting procedure is unnecessary.'

Conditioning

The test specimens were conditioned for at least 24 hours in the standard atmosphere of 60 ± 5 % relative humidity (R.H.) and 20 ± 2 °C.

Testing

Three specimens from both length and width were tested in accordance with BS EN ISO 15025: Procedure A (surface ignition):2002. The sample was tested at 18°C and 40% relative humidity (R.H.).

Each specimen was subjected to an applied flame using butane and a 15 second flame application time. The results obtained (shown in the table below) were assessed according to the requirements of BS 5867: Part 2:2008 (2015).

Test results relate only to the sample tested.

The results for all tests are given in the table(s) on the following page(s).

Reported by:..s

Lab Technician

Countersigned By:...

P Doherty

Executive Manager

Enquiries concerning this report should be addressed to Customer Services





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0)113 259 1999

Email: <u>info@bttg.co.uk</u> Website: www.bttg.co.uk

Date: 26 November 2018

Our Ref: 55742-3 Your Ref: 1644

Page: 3 of 3

Kobefab International B.V.

RESULTS

Sample Ref: Oster CS, stated to be 100% Trevira CS

BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds

Testing as received.

	Length			Width		
Specimen No.	1	2	3	4	5	6
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris separated	No	No	No	No	No	No

Requirements

Any "Yes" means fail except if only one specimen fails a further 6 specimens are tested, it the second 6 specimens all pass the result is a pass.

Result: Pass

Conclusion

The fabric meets the Type B performance requirements of BS 5867: Part 2: 2008.

The material should be identified with the manufacturers name, trademark or other identifying mark, the statement 'Flammability complies with the requirements of BS 5867: Part 2, Type B and instructions of any special precautions to be taken concerning care (including cleansing) of the curtain, drape or window blind to be manufactured from the fabric, preferably using an appropriate care labelling symbol in accordance with BS EN 23758 and taking account of the pre-treatment used in this test and the requirements of Clause 4 of BS 5867: Part 2: 2008 (2011). If the fabric is unsuitable for cleansing, this shall be stated.

Note: This report relates only to the samples submitted and as described in the report.

Uncertainty Budget

There is no uncertainty budget associated with BS 5867: Part 2: Type B as no measurements are determined, the pass/fail criteria is assessed visually.

