



## TEST REPORT

**Client:** Kobefab International BV  
De Vest 62  
5555 XP Valkenswaard  
The Netherlands

**Entry No:** 76556

**Date received:** 22/06/2016

**Client's Description:** Sample of fabric: Cheetah also representing Antelope, Impala & Topi

**Test Required:** Flammability in accordance with BS 5852 ignition source 5

**Pre-treatment:** Water soaking in accordance with BS5852:2006 Annex E followed by Line drying

**Conditioning:** A minimum of 96 hours at 50+/-5% Relative Humidity, 23+/-2°C

**Date Tests Completed:** 12/07/2016

**Method of Test:** BS 5852: 2006 Clause 11 (composites)

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
5 (Wood Crib)	Flaming ceased within the specified ten minute period after ignition of the crib and no progressive smouldering occurred.	PASS

**Note:** A 35 kg/m<sup>3</sup> CMHR foam (Carpenters RX36-125) was used as the filling

-----End of Page-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein*



Dale Brockbank  
Materials Testing Manager  
15 July 2016

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
  - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
  - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104

**Client:** Kobefab International BV

**Entry No:** 76556



During the tests the following data was recorded: -

**Source 5**

<b>Time of ignition (sec)</b>	13	15
<b>Time to extinction of flaming (sec)</b>	355	371
<b>Time to extinction of smoke (sec)</b>	477	482
<b>Time to cover splitting (sec)</b>	173	121
<b>Damage on seat width (mm)</b>	156	161
<b>Damage on seat length (mm)</b>	76	78
<b>Damage on seat depth (mm)</b>	27	24
<b>Damage on back width (mm)</b>	149	173
<b>Damage on back length (mm)</b>	414	396
<b>Damage on back depth (mm)</b>	48	37
<b>Melting (Yes or No)</b>	Yes	Yes
<b>Dripping (Yes or No)</b>	No	No
<b>Charring (Yes or No)</b>	Yes	Yes

-----End of Document-----